

AD

AD 669240



DDC  
REFRAME  
MAY 20 1968  
RECEIVED  
C

Reproduced by the  
CLEARINGHOUSE  
for Federal Scientific & Technical  
Information Springfield Va. 22151

Watertown, Massachusetts 02172

AMMRC TR 68-08

**SOME EFFECTS OF POWDER PARTICLE SIZE ON  
THE PHYSICAL BEHAVIOR OF PRESS-FORGED  
BERYLLIUM**

Technical Report by  
*JACOB GREENSPAN*

May 1968

This document has been approved for public  
release and sale; its distribution is unlimited.

D/A Project 1C024401A328  
AMCMS Code 5025.11.294  
Metals Research for Army Materiel  
Subtask 38166

PROTOTYPES LABORATORY  
ARMY MATERIALS AND MECHANICS RESEARCH CENTER  
WATERTOWN, MASSACHUSETTS 02172

ARMY MATERIALS AND MECHANICS RESEARCH CENTER

SOME EFFECTS OF POWDER PARTICLE SIZE ON THE PHYSICAL BEHAVIOR  
OF PRESS-FORGED BERYLLIUM

ABSTRACT

Powder metallurgy beryllium generally contains an oxide dispersoid, due to particle surface scale, and thus the material actually is a system subject to particle strengthening. The present report shows a dependence of strength on raw powder particle size and also on thermal history.

## INTRODUCTION

Powder metallurgy beryllium differs from ingot beryllium particularly in oxide content and, as a result, microstructures of the massive materials differ significantly.<sup>1</sup> In general, the oxide appears as a dispersoid in network-like configuration, distributed throughout. Principally, it has been known to act as a barrier to grain growth, characterizing powder metallurgy material by grain size considerably finer than that of ingot material. An important result has been grain refinement strengthening and, in addition, dispersed particles have shown some influence on fundamental deformation behavior of the matrix material. Thus, the dispersoid, which actually occurs inadvertently as a result of powder surface oxidation, is known to be particularly relevant to mechanical behavior and is recognized as an important materials parameter. However, more exact characterization is necessary for more effective utilization and greater understanding of the particle-matrix relationship will be helpful to further guidance. The present report gives some experimental data that contribute in part to the subject.

## PROCEDURE

The material examined in this investigation was an industrial-grade electrolytic powder, having the impurity analysis shown in Table I. Powders

Table I. IMPURITY ANALYSIS OF  
ELECTROLYTIC BERYLLIUM POWDER

Impurity	ppm	Impurity	ppm	Impurity	ppm	Impurity	ppm
Iron	300	Sodium	<100	Silicon	25	Copper	7
Carbon	260	Zinc	< 80	Titanium	<25	Silver	<3
Chlorine	200	Calcium	30	Lead	<15	Cadmium	<2
Nickel	140	Chromium	25	Molybdenum	<15	Boron	<1
Aluminum	110	Magnesium	25	Manganese	11		
BeO 1.91% for -43 micron powder; 2.2% for -20 micron powder							

were attritioned by conventional procedure, and then were sized nominally to fractions of -43 micron and -20 micron particles. The object in this case was to alter oxide distribution without large change in oxide content. The actual increase was from 1.91 to 2.2 percent (Table I) by removing the 43 to 20 micron fraction of metal powder in this way. The powders were hot pressed to block, and then cubes of 2-inch dimension were press forged to 1/2-inch plate as shown in Figure 1. Forging was performed at specific temperatures as given in Table II, and then additional heat treatment, associated with solution and precipitation of certain metallic impurities, was applied.<sup>2-7</sup> Possible changes of this kind were followed by precision electrical resistivity measurement along the gage length of tensile coupons of 1-inch length (about 2.5 cm) and about 0.030-square inch cross section, (about 19 sq mm) later tested in tension. Measurement was at room temperature only, the object being to note relative changes that might associate metallic impurity with mechanical behavior. The resistivity measurement was accomplished with a Kelvin bridge capable of  $10^{-6}$  ohm resolution, but it was found that general experimental deviation of the order of 1 percent of the mean could occur.




Figure 1. PRESS-FORGED BERYLLIUM, SHOWING STARTING BLOCK AND PLATE FORGED AT VARIOUS TEMPERATURES

19-066-1778/AMC-45

The possible influence of the above-described variations on uniaxial tensile properties, impact behavior, and hardness then was examined. Tensile samples of the size indicated were tested with an extensometer attached, duration of the test being of the order of minutes. Impact test bars, in smooth simple-beam configuration, were struck by a swinging pendulum and the total energy for fracture was recorded. Samples were of 0.394-inch square cross section (about 1 cm) and 1-5/8-inch span (about 4 cm), and the estimated rise time to fracture was of the order of milliseconds. Finally, hardness indentations of Rockwell B nomenclature were taken on both tensile and impact test samples.

## RESULTS

Impact strength was found to be influenced by powder particle size as indicated in Figure 2. The -20 micron material exhibited considerably greater resistance to impact than the -43 micron material, but this behavior was confined to the lower end of the processing temperature scale employed. Heating

Table II. PHYSICAL PROPERTIES OF  
FORGED ELECTROLYTIC BERYLLIUM POWDER BLOCK

Forging Temperature		Additional Thermal Treatment	Impact Energy* (ft-lb)		Strength Properties†						Rockwell B Hardness‡		Resistivity** (microhm cm)	
					-20 μ			-43 μ						
					Y.S.	T.S.	Elong.	Y.S.	T.S.	Elong.				
deg F	deg C		-20 μ	-43 μ	(ksi)	(ksi)	(%)	(ksi)	(ksi)	(%)	-20 μ	-43 μ	-20 μ	-43 μ
1400	762	As forged	30.8	22.5	54.1	85.8	18	34.9	65.2	6.0	91.2	90	4.28	4.48
		Aged††	4.2	5.4	42.1	64.2	2	32.9	64.2	5.0	88.0	87	4.27	4.25
1600	871	Solutionized††											4.30	4.40
													4.52	4.08
1800	982	As forged	31.0	14.5	41.6	71.9	7	44.9	70.6	8.0	89.2	88.5	4.58	3.91
		Aged	4.0	8.6	35.5	66.9	5	39.8	57.1	1.0	87.5	86.5	4.49	4.18
1900	1038	Solutionized											4.42	4.09
													4.46	3.90
1900	1038	As forged	16.8	9.5	35.1	69.4	5	36.2	70.8	12.0	87.0	86.0	4.46	4.06
		Aged	7.0	7.3	33.8	62.4	4	36.2	64.5	3.0	86.2	85.5	4.61	4.06
1900	1038	Solutionized											4.32	4.18
													4.46	4.07
1900	1038	As forged	13.0	12.1	36.7	70.6	10	31.4	68.2	3.7	85.5	85.5	4.46	4.07
		Aged	9.5	8.9	34.8	73.0	11	28.5	60.7	4.6	86.0	85.0	4.48	4.25

Heat treatment: Homogenized, 1900 F (1038 C), in vacuum, 6 hours, cooled in flowing argon, before forging.

\*Smooth test bars. Average of at least two observations.

†Average of two observations.

‡Average of at least four observations.

\*\*Average of at least six observations.

††1400 F (762 C) in vacuum, 8 hours, furnace cooled.

††1900 F (1038 C) in vacuum, 6 hours, cooled in flowing argon.

at higher temperatures, whether for forging or other thermal treatment, is seen generally to have nullified the effect. Tensile strength, given in Figure 3 shows trends of the same kind, but to far lesser extent on the respective ordinate scales employed. This behavior is reflected also for hardness, given in Figure 4. It is seen that the -20 micron material was always the harder by a small but measurable increment, and that the general loss in strength associated with thermal history was accompanied by loss in hardness.

In general, the higher values of impact strength were coincident with a greater degree of plastic deformation on impact. The limits experienced are illustrated in Figure 5 with samples of about 30 and 3 foot-pound impact strength level. While the difference in plastic deformation appears small in the figure, the numerical difference in absorbed impact energy




Figure 2. IMPACT RESISTANCE OF  
FORGED BERYLLIUM POWDER BLOCK  
19-064-323/AMC-48




Figure 3. YIELD AND TENSILE STRENGTHS OF FORGED BERYLLIUM POWDER BLOCK

19-066-319/AMC-48




Figure 4. HARDNESS OF FORGED BERYLLIUM POWDER BLOCK

19-066-324/AMC-48

is seen to have been relatively great. Thus, it seems reasonable that further marginal increases in ductility could be of magnified significance to impact behavior of this kind. Fracture markings in all samples were indicative generally of brittle fracture as shown by a typical macrofractograph in Figure 6. Yet, some change toward a more "ductile" appearance, as well as the appearance of some crack arrest, is observed on the compression side of the test bar. For beryllium, it is known that suppression of fracture can result in increased slip activity, and the preceding probably is such an example.

Photomicrographs showing dispersoid (in bright light) and grain structure (in polarized light) are presented in Figure 7. This metallography shows little distinction between the two powder materials with respect to general dispersoid configuration, but it is known that very small oxide particles must be more profuse in the -20 micron material. Also, grain sizes appear nearly equivalent, and it is significant that the relatively large differences in impact strength were not accounted for by this factor.

Precision electrical resistivity data given in Table II show that the metallic impurity present (Table I), did not undergo solutionizing and aging reactions that resulted in measurable changes in the electrical resistivity. This is concluded from the general lack of distinction between aged and solu-

tionized conditions, as well as between the processing temperatures shown. Considerable variability between some groups is seen, but without specific relation to mechanical behavior. This might be an indication that the distribution of impurity in the parent block material was not uniform, although the extent involved is insensitive to the present mechanical testing.





Figure 5. DUCTILITY IN BERYLLIUM IMPACT TEST BARS  
19-066-321/AMC-68




Figure 6. TYPICAL MACROFRACTOGRAPH.  
BERYLLIUM IMPACT TEST BAR  
19-066-320/AMC-68

With metallic impurity seen to have been of negligible consequence, within the present scope, mechanical behavior must have been influenced principally by the oxide dispersoid. Results are as though they were influenced by a condition of continuity or adhesion between particle and matrix that was subject to disruption by the temperature experienced, the effect increasing with temperature. Loss of this adhesion should not affect resistivity measurably, but should affect strength, which is exactly in accordance with the data that have evolved. Thus, the possibility of some form of continuity between the beryllia particle and the beryllium matrix, though apparently unusual, is indicated.





30 ft-lb Impact Energy



Bright Light

3 ft-lb Impact Energy

Polarized Light

Figure 7. MICROSTRUCTURES OF BERYLLIUM IMPACT TEST BARS.  
Left shows dispersoid, right shows grain structure. Mag. 500X.

19-066-322/AMC-48

#### SUMMARY AND REMARKS

The oxide dispersoid in powder metallurgy beryllium, which is known to be an important constituent with respect to mechanical behavior, was related further with strength, hardness, and process history. The dispersoid was seen to have been influential beyond its effect in grain refinement strengthening. Further understanding should lead to more effective use of the parameters involved. The possibility of some form of adhesion between particle and matrix has been indicated, though this concept of a nondeformable particle, particularly of the beryllia-beryllium system, appears unusual. Unquestionably, the particle must play a fundamental role in the fracture process, in crack origin as well as crack propagation. Particles are not in uniform dispersion, but are concentrated in network-like zones, predominantly in the vicinity of grain boundaries, as indicated in Figure 7. These zones are in greater resemblance to the aggregate structure of this class of materials than the disperse structure, which in itself is seen to be a strengthening factor.<sup>8,9</sup> If crack origin is at grain boundaries, as has been indicated in some bicrystal studies,<sup>10</sup> then the role of the dispersoid is emphasized. However, electron micrography in other work has shown very small oxide particles, in considerable numbers, within grains also.<sup>11</sup> Apart from these observations that indicate the need for understanding of particle-matrix relationships, additional empirical data, based on methods generally employed for this class of dispersion-strengthened system, may lead to significant development of powder metallurgy beryllium.

#### ACKNOWLEDGMENT

The author is grateful to Dr. K. J. Tauer and Mr. L. R. Aronin of AMRC for helpful discussions regarding electrical resistivity measurement and interpretation of data.

#### LITERATURE CITED

1. HAUSNER, H. H. *Powder Metallurgy of Beryllium*. Chapter A, from "Beryllium, its Metallurgy and Properties", U. of Cal. Press, 1965.
2. MASH, D. R. *Aging Effects in Beryllium*. Trans. AIME, v. 203, 1955, p. 1235.
3. GELLES, S. H. *Aging Effects in Beryllium*. J. Metals, v. 12, 1960, p. 789.
4. ROOKSBY, H. P. *Intermetallic Phases in Commercial Beryllium*. J. Nuclear Materials, v. 7, no. 2, 1962, p. 205.
5. MEREDITH, J. E. and SANKILL, J. *A Precipitation Reaction in Commercially Pure Beryllium*. Chapman and Hall, 1963.
6. CARRABINE, J. A. *Ternary Phases in Commercial Beryllium*. J. Nuclear Materials, v. 8, no. 2, 1963.
7. MOORE, A. *Mechanical Properties of Beryllium as Affected by Heat Treatment Above 700 C.* J. Nuclear Materials, v. 3, no. 1, 1961, p. 113.
8. GUARD, R. W. *Mechanisms of Fine Particle Strengthening*. Chapter 9, "Strengthening Mechanisms in Solids", ASM, 1962.
9. GRANT, N. J. *Dispersion Strengthening*. Chapter 3, "Strengthening Mechanisms", Twelfth Sagamore Army Materials Research Conference, 1965.
10. ARONIN, L. R., DAMIANO, V. V., et al. *Beryllium Bicrystal Studies*. AFML-TR-65-252, June 1966.
11. MORICEAUX, J., LOGEROT, J. M., and CROUTZEILLES, M. *Influence of the Distribution of Oxide and of the Total Impurity Level on Recrystallisation and Grain Growth of Beryllium*. ASD-TDR-62-509, February 1965.

## TECHNICAL REPORT DISTRIBUTION

No. of Copies	To
	Office of the Director, Defense Research and Engineering, The Pentagon, Washington, D. C. 20301
1	ATTN: Mr. John C. Barrett, Rm. 3D-1085
20	Commander, Defense Documentation Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, Virginia 22314
1	Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio 43201
	Chief of Research and Development, Department of the Army, Washington, D. C. 20310
2	ATTN: Physical and Engineering Sciences Division
	Commanding General, Army Research Office (Durham), Box CM, Duke Station, Durham, North Carolina 27706
1	ATTN: Information Processing Office
	Commanding General, U. S. Army Materiel Command, Washington, D. C. 20315
1	ATTN: AMCRD-RC-M
	Commanding General, Deseret Test Center, Fort Douglas, Utah 84113
1	ATTN: Technical Information Office
	Commanding General, U. S. Army Electronics Command, Fort Monmouth, New Jersey 07703
2	ATTN: AMSEL-RD-MAT
	Commanding General, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809
1	ATTN: Technical Library
	Commanding General, U. S. Army Munitions Command, Dover, New Jersey 07801
1	ATTN: Technical Library

No. of Copies	To
1	Commanding General, U. S. Army Satellite Communications Agency, Fort Monmouth, New Jersey 07703 ATTN: Technical Document Center
2	Commanding General, U. S. Army Tank-Automotive Command, Warren, Michigan 48090 ATTN: SMOTA-RTS, Tech Data Coord Br
1	Commanding General, U. S. Army Weapons Command, Research and Development Directorate, Rock Island, Illinois 61201 ATTN: AMSWE-RDR
1	Commanding General, White Sands Missile Range, New Mexico 88002 ATTN: STEWS-WS-VT
1	Commanding Officer, Aberdeen Proving Ground, Maryland 21005 ATTN: Technical Library, Building 313
1	Commanding Officer, Frankford Arsenal, Bridge and Tacony Streets, Philadelphia, Pennsylvania 19137 ATTN: Library Branch C 2500
1	Commanding Officer, Department of the Army, Ohio River Division Laboratories, Corps of Engineers, 5851 Mariemont Avenue, Cincinnati, Ohio 45227 ATTN: ORDLB-TR
1	Commanding Officer, Picatinny Arsenal, Dover, New Jersey 07801 ATTN: SMUPA-VA6
4	Commanding Officer, Redstone Scientific Information Center, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809 ATTN: AMSMI-RBLD, Document Section
1	Commanding Officer, Watervliet Arsenal, Watervliet, New York 12189 ATTN: SNEWV-RDT, Technical Information Services Office
1	Commanding Officer, U. S. Army Aviation Materiel Laboratories, Fort Eustis, Virginia 23604
1	Commanding Officer, U. S. Army Aviation School Library, Fort Rucker, Alabama 36360 ATTN: USAAVNS-P&NRI
2	Commanding Officer, USACDC Ordnance Agency, Aberdeen Proving Ground, Maryland 21005 ATTN: Library, Building 305

No. of  
Copies

To

Commanding Officer, U. S. Army Engineer School,  
Fort Belvoir, Virginia 22060

1 ATTN: Library

Director, Naval Research Laboratory, Anacostia Station,  
Washington, D. C. 20390

1 ATTN: Technical Information Officer

Chief, Office of Naval Research, Department of the Navy,  
Washington, D. C. 20315

1 ATTN: Code 423

Air Force Materials Laboratory, Wright-Patterson Air Force Base,  
Ohio 45433

2 ATTN: AFML (MAA)

1 AFML (MAT)

1 AFML (MAM)

1 AFML (MAN)

1 U. S. Atomic Energy Commission, Office of Technical Information  
Extension, P. O. Box 62, Oak Ridge, Tennessee 37830

National Aeronautics and Space Administration, Washington, D. C. 20546

1 ATTN: Mr. B. G. Achhammer

1 Mr. G. C. Deutsch

1 Mr. R. V. Rhode

National Aeronautics and Space Administration, Marshall Space Flight  
Center, Huntsville, Alabama 35812

1 ATTN: R-P&VE-M, Dr. W. R. Lucas

1 M-F&AE-M, Mr. W. A. Wilson, Building 4720

National Academy of Sciences, Materials Advisory Board, 2101 Constitution  
Avenue, N. W., Washington, D. C. 20418

1 ATTN: Dr. J. R. Lane

Commanding General, Army Materials and Mechanics Research Center,  
Watertown, Massachusetts 02172

5 ATTN: AMXMR-AT

1 AMXMR-AA

1 AMXMR-RP

1 AMXMR-RX

1 Author

73 TOTAL COPIES DISTRIBUTED

UNCLASSIFIED  
Security Classification

DOCUMENT CONTROL DATA - R&D (Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1. ORIGINATING ACTIVITY (Corporate author) Army Materials and Mechanics Research Center Watertown, Massachusetts 02172		2a. REPORT SECURITY CLASSIFICATION Unclassified
		2b. GROUP
3. REPORT TITLE SOME EFFECTS OF POWDER PARTICLE SIZE ON THE PHYSICAL BEHAVIOR OF PRESS-FORGED BERYLLIUM		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates)		
5. AUTHOR(S) (Last name, first name, initial) Greenspan, Jacob		
6. REPORT DATE May 1968	7a. TOTAL NO. OF PAGES 8	7b. NO. OF REFS 11
8a. CONTRACT OR GRANT NO.	9a. ORIGINATOR'S REPORT NUMBER(S) AMMRC TR 68-08	
a. PROJECT NO. 1C024401A328 c. AMCMS Code 5025.11.294 d. Subtask 38166	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
10. AVAILABILITY/LIMITATION NOTICES This document has been approved for public release and sale; its distribution is unlimited.		
11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY U. S. Army Materiel Command Washington, D. C. 20315	
13. ABSTRACT Powder metallurgy beryllium generally contains an oxide dispersoid, due to particle surface scale, and thus the material actually is a system subject to particle strengthening. The present report shows a dependence of strength on raw powder particle size and also on thermal history. (Author)		

DD FORM 1 JAN 64 1473

UNCLASSIFIED  
Security Classification

**UNCLASSIFIED**  
Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Beryllium Cracking Dispersoids Hardness Impact strength Ingots Mechanical properties Microstructure Oxides Particle size Powder metallurgy Tensile properties Thermal history						

**INSTRUCTIONS**

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, &c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).

10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through \_\_\_\_\_."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through \_\_\_\_\_."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through \_\_\_\_\_."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (*paying for*) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.

**UNCLASSIFIED**  
Security Classification